

Technical Leaflet

WorléeKyd MH 439

Art.-No. 111000-00532

Revision: 31.10.03

W´Kyd MH 439 is a short oil, fast drying alkyd resin based on special fatty acids for the production of air and forced drying primers and top coats, also for low aromatic containing paints.

Technical Data:

Content of phthalic anhydride	approx. 32%
Oil content	approx. 39%
Oil type	special fatty acids
Content of hard resin	approx. 7%
Colour, Gardner, 50% in xylene, DIN ISO 4630	max. 10
Acid value, DIN EN ISO 3682	max. 25
Viscosity, 20 °C, 50% in xylene, DIN 53211-4	100 - 130 sec.
Delivery form	60% in xylene

Compatibility:

W´Kyd MH 439 is compatible with most short oil and medium oil length alkyd resins. It is also compatible with some physical drying binders like vinyl mix polymerisates (e.g. Laroflex from BASF) and chlorinated rubber (e.g. Pergut from Bayer).

Solubility:

W´Kyd MH 439 is well soluble in aromatics, esters, ketones and glycol ether esters. In white spirit W´Kyd MH 439 is partially soluble.

Application and Properties:

W´Kyd MH 439 has mainly been developed for good drying primers and top coats.

Due to the very good compatibility with physical drying binders, W´Kyd MH 439 can also be used for fast drying and high resistant industrial enamels.



WorléeKyd MH 439

2

Drying:

The following addition of driers is recommended:

0.04 - 0.06 % Co metal
0.05 - 0.10 % Zr metal
0.20 - 0.25 % Ca metal
calculated on 100 % alkyd resin