

Technical Leaflet

WorléeCryl 7120

Art.-No. 212052-01036

Revision: 09.11.09

Styrene acrylic copolymer emulsion.

Technical Data:

Non volatile content DIN EN ISO 3251	49% ± 1
pH - value DIN ISO 976	8.2 - 9.0
Density DIN EN ISO 2811-1	approx. 1.09 g/cm ³
Viscosity Brookfield, 20 °C, DIN EN ISO 2555	200 - 800 mPa·s
Emulsion system	anionic
MFFT Minimum film forming temperature ISO 2115	15 °C
Freeze-/thaw stability	protect from freezing
Delivery form	49% in water

Outstanding Characteristics:

Excellent adhesion on blanc and zined steel.

Excellent weather stability.

Properties and Application:

Due to its excellent weather resistance W'Cryl 7120 can be used for the production of **rust inhibitive primers on metal**.

The storage stability in the originally closed barrel is at a storage temperature from + 5 to + 25 °C six months, counted from the day of the delivery ex works.