

Technical Leaflet

WorléeCryl 7189

Art.-No. 212052-01056

Revision: 09.11.09

Methacrylic copolymer emulsion.

Technical Data:

Non volatile content DIN EN ISO 3251	49% ± 1
pH-value DIN ISO 976	7.0 - 8.0
Density, 20 °C, DIN EN ISO 2811-1	approx. 1.08 g/cm ³
Viscosity, 20 °C, Brookfield, DIN EN ISO 2555	max. 200 mPa·s
Emulsion system	anionic
MFFT Minimal film forming temperature ISO 2115	16 °C
Freeze-/thaw stability	protect from freezing
Delivery form	49% in water

Outstanding Characteristics:

Excellent compatibility with alkali and cement .

High flexibility.

Properties and Application:

W`Cryl 7189 is a binder for the production of synthetic resin-bound renderings, wall paints, flagstone- and building adhesives. The product features a high initial adhesion and a very fast setting.

W`Cryl 7189 can also be used for the production of sealing compounds.

The storage stability in the originally closed barrel is at a storage temperature from + 5 to + 25 °C six months, counted from the day of the delivery ex works.