

Technical Leaflet

Revision: 22.01.04

WorléeCryl L 1870

Art.-No. 112003-06257

Beschreibung

W´Cryl L 1870 is a physical drying thermoplastic acrylic resin.

Technical Data

Standard solvent	55% in special mineral spirit 80/110
Viscosity, 20 °C, DIN EN ISO 2555	max. 3,000 mPa·s
Density, 20 °C, DIN EN ISO 2811-1	0.87 g/cm ³
Non volatile content, DIN EN ISO 3251	54 - 56%
Glass transition temperature (T _g)	approx. 17 °C
Colour, Gardner, DIN ISO 4630	approx. 1
Flash point DIN EN 22719	< 0 °C