

Technical Leaflet

WorléeCryl L 2380

Art.-No. 112003-08193

Revision: 18.02.05

W´Cryl L 2380 is a physically drying thermoplastic acrylic resin for different coating systems, for improving hardness, gloss and adhesion.

Technical Data:

Non volatile content, 1h/125 °C, DIN EN ISO 3251	50% ± 1
Acid value, on solids, DIN EN ISO 3682	max. 3
Colour, Gardner, delivery form, DIN ISO 4630	max. 3
Viscosity, Brookfield, 20 °C, delivery form, DIN EN ISO 2555	approx. 500 mPa·s
Glass transition temperature	83 °C
Delivery form	50% in deaomat. HC 160 - 200

Compatibility:

W´Cryl L 2380 is compatible with alkyd resins.

Solubility:

W´Cryl L 2380 is soluble in ketones, esters, aromatic and deaomatized hydrocarbons as well as isoparaffines. W´Cryl L 2380 is insoluble in alcohols and water.