

Technical Leaflet

WorléeKyd BSA 5015

Art.-No. 111014-14166

Revision: 16.03.12

W`Kyd BSA 5015 is a low viscous, air drying special modified alkyd resin mainly for the use in **low VOC** industrial and house paints with good resistance properties.

Technical Data:

Non volatile content, 1h/125 °C, DIN EN ISO 3251	85% ± 1
Oil type	special vegetable fatty acid
Oil content	approx. 49%
Acid value, on solids, DIN EN ISO 3682	max. 12
Colour, Gardner, 60% in dearomat. HC 160 - 200, DIN ISO 4630	max. 5
Flow time, 60% in dearomat. HC 160 - 200, DIN 53211-4	40 - 60 s
Delivery form	85% in dearomat. HC 160 - 200