

Technical Leaflet

WorléeSol NW 474

Art.-No. 111055-12273

Revision: 25.04.2013

W'Sol NW 474 is a long oil amine and co-solvent free alkyd emulsion.

Technical Data:

Non volatile content, 1h/125 °C, DIN EN ISO 3251	60% ± 2
Oil content	approx. 74%
Viscosity, 20 °C, delivery form, Brookfield, spindle 4/20 rpm, DIN EN ISO 2555	max. 1,500 mPa·s
pH-value, delivery form, DIN EN ISO 976	2 - 5
Density, 23 °C, DIN EN ISO 2811-1	1.013 g/cm ³
Appearance	white, milky liquid
Delivery form	60% in water

Applications and Properties:

W'Sol NW 474 is suitable for the manufacture of wood impregnations and -glazings.
A further application field for W'Sol NW 474 is open time and body improvement of decorative and house paints based on W'Sol E 150 W by addition of 3 - 10 % on total formulation.

Recommended Storage and Transport Conditions:

5 to 25 °C.
Protect against freezing and direct sunlight.