

Technical Leaflet

WorlérThix 670 hs

Art.-No. 111030-15028

Revision: 16.03.12

W^lThix 670 hs is a thixotropic long oil alkyd resin, mainly for the manufacture of primers, fillers, gloss paints and silk gloss paints, **low VOC**.

Technical Data:

Non volatile content, 1h/125 °C, DIN ISO EN 3251	70% ± 2
Content of phthalic anhydride	approx. 21%
Oil type	special mixed fatty acids
Oil content	approx. 61%
Acid value, on solids, DIN EN ISO 3682	max. 15
Colour, Gardner, delivery form, DIN ISO 4630	max. 10
Viscosity, 20 °C	thixotropic gel
Delivery form	70% in dearomatized HC 180 - 220

Storage:

The storage stability in the originally closed barrel is at a storage temperature from + 5 to + 25 °C 6 months, counted from the day of the delivery ex works.